



Designation: D448 – 12 (Reapproved 2017)

Standard Classification for Sizes of Aggregate for Road and Bridge Construction¹

This standard is issued under the fixed designation D448; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This classification defines aggregate size number designations and standard size ranges for mechanical sieve analyses of coarse aggregate and screenings for use in the construction and maintenance of various types of highways and bridges.

1.2 *Units*—The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

NOTE 1—Sieve size is identified by its standard designation in Specification E11. The alternative designation given in parentheses is for information only and does not represent a different standard sieve size.

1.3 The text of this classification references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the classification.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[C136 Test Method for Sieve Analysis of Fine and Coarse Aggregates](#)

¹ This classification is under the jurisdiction of ASTM Committee D04 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.50 on Aggregate Specifications.

Current edition approved Oct. 1, 2017. Published October 2017. Originally approved in 1937. Last previous edition approved in 2012 as D448 – 12. DOI: 10.1520/D0448-12R17.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[D8 Terminology Relating to Materials for Roads and Pavements](#)

[D75 Practice for Sampling Aggregates](#)

[E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves](#)

3. Terminology

3.1 For definitions of terms, see Terminology [D8](#).

4. Significance and Use

4.1 Some contract documents specify certain aggregate sizes for specific uses or may suggest one or more of these sizes as appropriate for the preparation of various end-product mixtures. In some cases, closer limits on variability of the aggregate grading are required.

5. Manufacture

5.1 The standard sizes of aggregate described in this classification are manufactured by means of any suitable process used to separate raw material into the desired size ranges. Production of standard sizes by blending two or more different components is permitted.

6. Standard Sizes

6.1 Standard aggregate sizes shall conform to the requirements prescribed in [Table 1](#) for the size number specified. Conformance shall be determined by means of laboratory sieves having square openings and conforming to Specification [E11](#).

7. Basis of Classification

7.1 Classification of an aggregate is based upon the size number designation and size ranges shown in [Table 1](#). Aggregate shall be sampled in accordance with Practice [D75](#) and tested for grading by Test Method [C136](#).



TABLE 1 Standard Sizes of Processed Aggregate

Size Number	Nominal Size, Square Openings	Amounts Finer than Each Laboratory Sieve (Square Openings), mass percent														
		100-mm (4-in.)	90-mm (3½-in.)	75-mm (3-in.)	63-mm (2½-in.)	50-mm (2-in.)	37.5-mm (1½-in.)	25.0-mm (1-in.)	19.0-mm (¾-in.)	12.5-mm (½-in.)	9.5-mm (¾-in.)	4.75-mm (No. 4)	2.36-mm (No. 8)	1.18-mm (No. 16)	300-µm (No. 50)	150-µm (No. 100)
1	90 to 37.5-mm (¾ to 1½-in.)	100	90 to 100	...	25 to 60	...	0 to 15	...	0 to 5
2	63 to 37.5-mm (2½ to 1½-in.)	100	90 to 100	...	0 to 15	...	0 to 5
24	63 to 19.0-mm (2½ to ¾-in.)	100	90 to 100	...	25 to 60	...	0 to 10	0 to 5
3	50 to 25.0-mm (2 to 1-in.)	100	0 to 15	35 to 70	...	0 to 5
357	50 to 4.75-mm (2-in. to No. 4)	100	35 to 70	...	10 to 30	0 to 5
4	37.5 to 19.0-mm (1½ to ¾-in.)	100	20 to 55	90 to 100	...	0 to 15	0 to 5
467	37.5 to 4.75-mm (1½-in. to No. 4)	100	...	95 to 100	...	35 to 70	10 to 30	0 to 5
5	25.0 to 12.5-mm (1 to ½-in.)	90 to 100	100	...	20 to 55	0 to 5
56	25.0 to 9.5-mm (1 to ⅝-in.)	90 to 100	100	...	40 to 85	0 to 15	0 to 5
57	25.0 to 4.75-mm (1-in. to No. 4)	100	...	10 to 40	0 to 15	0 to 5
6	19.0 to 9.5-mm (¾ to ⅝-in.)	0 to 5
67	19.0 to 4.75-mm (¾-in. to No. 4)	0 to 5	0 to 5
68	19.0 to 2.36-mm (¾-in. to No. 8)	90 to 100	20 to 55	0 to 10	0 to 5	0 to 5
7	12.5 to 4.75-mm (½-in. to No. 4)	0 to 15	0 to 5
78	12.5 to 2.36-mm (½-in. to No. 8)	100	40 to 70	0 to 15	0 to 5	0 to 5
8	9.5 to 2.36-mm (⅝-in. to No. 8)	0 to 10	0 to 10	0 to 5
89	9.5 to 1.18-mm (⅝-in. to No. 16)	0 to 10	0 to 10	0 to 5	0 to 5
9	4.75 to 1.18-mm (No. 4 to No. 16)	100	10 to 30	0 to 10	0 to 5	0 to 5	...
10	4.75-mm (No. 4 to 0 ^A)	85 to 100	10 to 40	0 to 10	0 to 5	0 to 5	...
		100	85 to 100	10 to 40	0 to 10	0 to 5	10 to 30

^A Screenings.

8. Keywords

8.1 aggregate standard size; coarse aggregate; screenings

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>